

1 (January 4, 2010)
2 When a portion of existing concrete is to be removed without replacement, care
3 shall be taken to remove to a clean line with a smooth surface of less than 1/16
4 inch profile obtained by methods of the Contractor's choice with the approval of the
5 Engineer. Steel reinforcing bars shall be cut a minimum of 1-inch behind the final
6 surface. The void left by removal of the steel reinforcing bar shall be coated with
7 epoxy resin and filled with mortar conforming to Section 9-20.4(2). The epoxy resin
8 shall be Type II conforming to Section 9-26.1 with the grade and class as
9 recommended by the resin manufacturer and as approved by the Engineer. The
10 mortar shall consist of cement and fine aggregate mixed in the proportions to match
11 the color of the existing concrete surface as nearly as practicable.