

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13

**(August 1, 2011)**  
**Material Transfer Vehicle**

Direct transfer of HMA from the hauling equipment to the paving machine will not be allowed in the top 0.30-feet of the pavement section of hot mix asphalt (HMA) used in traffic lanes with a depth of 0.08-feet or greater. A material transfer vehicle (MTV) shall be used to deliver the HMA from the hauling equipment to the paving machine. HMA placed in irregularly shaped and minor areas such as road approaches, tapers, and turn lanes are excluded from this requirement.

The MTV shall mix the HMA after delivery by the hauling equipment and prior to lay down by the paving machine. Mixing of the HMA shall be sufficient to obtain a uniform temperature throughout the mixture.