

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16

(August 3, 2009)

Strip Seal Expansion Joint System

The metal components shall conform to ASTM A 36, ASTM A 992, or ASTM A 572, and shall be protected against corrosion by one of the following methods:

1. Zinc metallized in accordance with Section 6-07.3 as supplemented in these Special Provisions.
2. Hot-dip galvanized in accordance with AASHTO M 111.
3. Paint in accordance with Section 6-07.3(9). The color of the top coat shall be Washington Gray. The surfaces embedded in concrete shall be painted only with a shop primer coat of paint conforming to Section 9-08.1(2)C.

The strip seal gland shall be continuous for the full length of the joint with no splices permitted, unless otherwise shown in the Plans.