

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12

(April 6, 2015)

Pre-formed fabric pads shall be composed of multiple layers of duck impregnated and bound with high quality oil resistant synthetic rubber compressed into resilient pads. The pre-formed fabric pads shall conform to the latest edition of MIL-C-882 and the following requirements. The number of plies shall be as required to produce the specified thickness, after compression and vulcanizing. Pre-formed fabric pads shall have a shore A hardness of  $90 \pm 5$  in accordance with ASTM D 2240.

Pre-formed fabric pads for seismic restrainers will be accepted based on the Manufacturer's Certificate of Compliance that the material furnished conforms to these specifications.