

1 ***(December 2, 2002)***

2 ***Epoxy Mortar***

3 Epoxy mortar shall be composed of one part of epoxy bonding agent, Type III, as
4 specified in Section 9-26.1, and two parts of clean, fine grained sand, by volume. The
5 grade and class of epoxy bonding agent shall be as recommended by the resin
6 manufacturer and approved by the Engineer.