

Aggregate Record of Field Test

Contract No.	Time/Date Sampled	Pit No.	
Acceptance No.	IA No.	Material Type	Quantity Represented
Total Wt. of Sample (before split)	Wt. of Wet Sample (gm)	Dry Wt. (gm)	Washed Dry Wt. (gm)

Method A

Sizes	Cummulative Wt. Retained (gm)	Cummulative % Retained	Reported % Passing	Specifications
6"				
4				
3				
2-1/2				
2				
1-1/2				
1-1/4				
1				
3/4				
5/8				
1/2				
3/8				
1/4				
No. 4				
8				
10				
16				
30				
40				
50				
80				
100				
200				

Sand Equivalent	
SE#1	_____
SE#2	_____
SE Avg.	_____
SE Specification	_____ Min.

Fracture	
Wt. of Fractured Particles (gm)	_____
Wt. of Unfractured Particles (gm)	_____
Wt. of Questionable Particles (gm)	_____
Percent Fracture	_____
Fracture Specification	_____ Min.

Moisture Content	
Wt. of Wet Sample (gm)	_____
Dry Wt. (gm)	_____
Wt of Moisture	_____
Percent Moisture Content	_____

Pan (gm) _____

Note: Round SEs up to the next whole number.
Round Percent Passing to the nearest whole number except #200 - round to the nearest 0.1%.

Formulas:

Sand Equivalent = (Sand Ht. / Clay Ht.) X 100
Percent Passing for Gradation = 100 - ((Wt. Retained / Dry Wt.) X 100)

Percent Fracture = $\frac{\text{Wt. of Fractured Particles} + (\text{Wt. of Questionable Fractured Particles} / 2)}{\text{Wt. of Fractured Particles} + \text{Unfractured Particles} + \text{Questionable Particles}} \times 100$

Moisture Content = $\frac{\text{Wt. of Wet Sample} - \text{Dry Wt.}}{\text{Dry Wt.}} \times 100$

Acceptance Action	<input type="checkbox"/> Conditionally Accepted	<input type="checkbox"/> Substandard Material	<input type="checkbox"/> Rejected
Qualified Tester	Date	Contractor	Date