

Naselle River Bridge 101/24

Chemical Sealers As Corrosion Inhibitors

WA-RD 105.1

Post-Construction Report
March 1987



Washington State Department of Transportation

Planning, Research and Public Transportation Division

in cooperation with the

United States Department of Transportation

Federal Highway Administration

Washington State Department of Transportation

Duane Berentson, Secretary
A.D. Andreas, Deputy Secretary
James P. Toohy, Assistant Secretary for Planning, Research and Public Transportation

Washington State Transportation Commission Research Committee

William O. Kamps, Chair
Richard Odabashian, Commissioner
Jerry Overton, Commissioner
Leo B. Sweeney, Commissioner

WSDOT Research Executive Committee

A.D. Andreas, Chair, Deputy Secretary for Transportation
E.W. Ferguson, District 4 Administrator
H. W. Parker, Assistant Secretary for Marine Transportation
Robert C. Schuster, Assistant Secretary for Highways
James P. Toohy, Assist. Sec. for Plan'g, Research & Public Transp.

WSDOT Research Technical Committees

Highway Operations and Development

Roland Cook, Chair, District 2 Administrator
John Aspaas, District 4 Project Engineer
William P. Carr, Associate Research Director
John Conrad, District 1 District Operations Engineer
Rich Darnell, District 3 Maintenance & Operations Engineer
C. Stewart Gloyd, Bridge/Structures Engineer
Wayne Gruen, State Traffic Engineer
Stan Moon, Location/Design Engineer
Ed Schlect, Construction Engineer - Paving
Don Senn, District 2 Location/Construction Engineer
Dick Shroll, District 6 Maintenance Superintendent
Ken Thomas, Operations Engineer, Bellingham Public Works Department
George Tsialis, Structural Engineer, Washington State University

Materials and Product Evaluation

Del Vandehey, Chair, State Construction Engineer
Keith W. Anderson, Federal Program Manager
Jim Buss, District 5 Construction Engineer
Newton Jackson, Pavement/Soils Engineer
Steve Kramer, Assistant Professor, Civil Engineering, U. of Washington
Bob Krier, Bridge Operations Engineer
Art Peters, Materials Engineer
Bob Spratt, District 2 Maintenance Engineer
John Strada, Construction Engineer - Grading

Planning and Multimodal

Don Tranum, Chair, District 6 Administrator
Ron Anderson, Manager, District 6 Management Services
Ken Casavant, Professor, Washington State University
King Cushman, Director, Pierce County Transit Development
Kris Gupta, Manager, Transportation Data Office
Kem Jacobson, District 1 Public Transportation & Planning Engineer
Jerry Lenzi, Manager, Multi Modal Branch
Jim Stakey, Manager, Public Transportation
Stephen Smith, Service Planning Manager, Ferry System, Colman Dock

WSDOT Research Implementation Committee

Stan Moon, Chair, Location/Design Engineer
Jack E. Hanson, Location Engineer
Dennis Ingham, Highway Maintenance Engineer
Kem Jacobson, District 1 Public Transportation and Planning Engineer
Bob Krier, Bridge Operations Engineer
Art Peters, Materials Engineer
Ed Schlect, Construction Engineer, Paving
Gerald Smith, District 1, Assistant I-90 Construction Engineer
Bob Spratt, District 2 Maintenance Engineer

WSDOT Research Office

John Doyle, Director
William P. Carr, Associate Director
Keith W. Anderson, Federal Program Manager
Julie Levenson, Database Coordinator
Ellen Loyer, Secretary
Carl Toney, Research Administrator

WSDOT Research Liaisons

District 1 - Kem Jacobson, Public Transportation and Planning Engineer
District 2 - Don Senn, Location/Construction Engineer
District 3 - Bob George, Assistant Location Engineer
District 4 - Richard N. Coffman, Maintenance Engineer
District 5 - Robert MacNeil, Design Engineer
District 6 - Richard Larson, Design and Planning Engineer
WSDOT Library - Barbara Russo, Librarian

Transportation Research Council

Transportation Commission

Vaughn Hubbard, Chair
William J. Kamps*#
Richard Odabashian*
Jerry B. Overton
Albert D. Rosellini
Bernice Stern
Leo B. Sweeney*

* Research Committee # Research Committee Chair

Federal Highway Administration

Paul C. Gregson, Division Administrator

Private Sector

Milton "Bud" Egbers, President, Skagit Valley Trucking
Richard Ford, Managing Partner, Preston, Thorgrimson, Ellis, Holman
William Francis, Vice President, Burlington Northern R.R.
Tom Gaetz, Project Manager, David Mowat & Company, Bellevue
Lawrence Houk, Vice President, Lockheed Shipbuilding
Charles H. Knight, President, Concrete Technology
H. Carl Munson, VP for Strategic Planning, Boeing Co., Seattle
Michael Murphy, President, Central Pre-Mix Concrete
Richard Norman, President, Associated Sand & Gravel, Everett
John Ostrowski, Public Works Director, Vancouver, WA
Richard S. Page, President, Washington Roundtable
James D. Ray, Senior Manager, IBM Company
Sudarshan Sathe, Director, Technical Services, Polycarb Inc., Cleveland, OH
Paul Turvil, General Manager, PACCAR, Technical Center, Mt. Vernon, WA

Universities

Gene L. Woodruff, Vice Provost for Research, UW
Robert V. Smith, Associate Provost for Research, WSU
Suninder K. Bhagat, Professor and Chair, Civil Engineering, WSU

Washington State Department of Transportation

Duane Berentson, Secretary
A.D. Andreas, Deputy Secretary
C.W. Beerman, District 5 Administrator
R.E. Bockstruck, District 1 Administrator
J.L. Clemen, Assistant Secretary for Mngt Services
R.C. Cook, District 2 Administrator
R.L. Daniels, Administrator, Public Affairs Office
E.W. Ferguson, District 4 Administrator
W.H. Hamilton, Assistant Secretary for Aeronautics
W.I. Hordan, State Aid Engineer
H.W. Parker, Assistant Secretary, Marine Transportation
R.C. Schuster, Assistant Secretary for Highways
J.H. Stakey, Manager, Public Transportation Office
J.P. Toohy, Assistant Secretary for Plan'g, Res., and Pub. Trans.
M.D. Tranum, District 6 Administrator
D.J. Vandehey, State Construction Engineer
A.T. Smelser, District 3 Administrator

Representative George Walk, Chair - Legislative Transportation Committee

Federal Highway Administration

M. Eldon Green, Region 10 Administrator
Otis C. Haseltin, Region Office Research and T2 Engineer
Ernest J. Valach, Director, Regional Planning and Program Development

Paul C. Gregson, Division Administrator
Barry Brecht, Division Office Programming and T2 Engineer
Charles W. Chappell, Division Transportation Planner

Washington State Transportation Center (TRAC) (UW and WSU)

G. Scott Rutherford, Director
Ken Casavant, Associate Director, WSU
Joe P. Mahoney, Associate Director, UW
Khosrow Babaei, Senior Research Engineer
Rhonda Brooks, Research Implementation Manager
Mark Hallenbeck, Senior Research Engineer
Ed McCormack, Research Engineer
Amy O'Brien, Coordinator
Bev Odgaard, Budget Analyst
Ron Porter, Word Processing Technician
Cy Ulberg, Senior Research Engineer
Cynthia Wallace, Clerk-Typist
Duane Wright, Research Aide

WASHINGTON STATE DEPARTMENT OF TRANSPORTATION
TECHNICAL REPORT STANDARD TITLE PAGE

1. REPORT NO WA-RD-105.1	2. GOVERNMENT ACCESSION NO	3. RECIPIENT'S CATALOG NO.	
4. TITLE AND SUBTITLE Chemical Sealers As Corrosion Inhibitors, Nasell River Bridge 101/24		5. REPORT DATE March 1987	
		6. PERFORMING ORGANIZATION CODE	
7. AUTHOR(S) C. A. Toney		8. PERFORMING ORGANIZATION REPORT NO	
		10. WORK UNIT NO.	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Washington State Department of Transportation Transportation Building Olympia, WA 98501		11. CONTRACT OR GRANT NO.	
		13. TYPE OF REPORT AND PERIOD COVERED Post Construction (Experimental May 1984 - March 1987)	
12. SPONSORING AGENCY NAME AND ADDRESS U.S. Department of Transportation Federal Highway Administration Washington, D.C. 20590		14. SPONSORING AGENCY CODE	
		15. SUPPLEMENTARY NOTES	
16. ABSTRACT <p>This Post Construction Report provides an overview of the selection of a chemical sealer and its use as a method of protecting the girders and piles of the Nasell River Bridge from the intrusion of chloride ions. The structure treated is located in a marine environment. Chem-Trete Silane sealer was used for this structure and applied as specified by the manufacture. After 1½ years exposure to a salt environment no deterioration of the concrete has been detected. Monitoring of the structure will continue under Washington State Department of Transportation's Bridge Inspection program.</p>			
17. KEY WORDS Sealer, Seal Coat Waterproofing, Concrete Sealer		18. DISTRIBUTION STATEMENT	
19. SECURITY CLASSIF. (of this report) Unclassified	20. SECURITY CLASSIF. (of this page) Unclassified	21. NO. OF PAGES 12	22. PRICE

CHEMICAL SEALERS AS CORROSION INHIBITORS

Naselle River Bridge 101/24

By

**Carl A. Toney
Research Administrator**

Post-Construction Report

Experimental Feature WA 82-02

**Prepared for
Washington State Transportation Commission
Department of Transportation
and in cooperation with
U.S. Department of Transportation
Federal Highway Administration**

March 1987

DISCLAIMER


The contents of this report reflect the views of the author who is responsible for the facts and the accuracy of the data presented herein. The contents do not necessarily reflect the official views or policies of the Washington State Department of Transportation or the Federal Highway Administration. This report does not constitute a standard, specification or regulation.

NOTICE

The Washington State Department of Transportation and the Federal Highway Administration do not endorse products or manufacturers. Trade or manufacturers' names appear herein solely because they are considered essential to the object of this report.

Contents

Vicinity Map.....	i
Purpose.....	1
Description.....	1
Construction Summary.....	3
Tests and Evaluations.....	4
Conclusions.....	5
Recommendations.....	6



Vicinity Map
Naselle River Bridge 101/24



Purpose:

The Washington State Department of Transportation (WSDOT), in search of a method for protecting concrete structures from the intrusion of chloride ions, identified the following chemical sealers from laboratory tested sealers reported in NCHRP Publication No. 244 as being the most effective in providing a chloride ion barrier:

- . Chem-Trete Silane
- . EA Sealer
- . Penetrating Sealer 1854

This experimental project was designed to provide field experience and an evaluation of the method of application and the effectiveness of one of the above sealers on newly constructed bridge girders and piles. Chem-Trete Silane was selected based on its excellent penetration and superior chloride ion barrier characteristics as reported in the NCHRP report.

Description:

The Naselle River Bridge (101/24) was selected as an appropriate structure for the chemical seal experiment due to its marine environment location. The bridge is located on

State Route 101, five miles north of the town of Naselle
(see vicinity map).

In addition to specified corrosion protection measures of epoxy coating all the reinforcing steel in both cast-in-place (CIP) concrete members and the prestressed girders and piles, all units were to receive a chemical seal surface treatment. The surface treatment was to be placed after the removal of the surface laitance by light sandblasting. Manufacture's specifications and rates of application were to be followed during the placement of the sealer. The sealer was to be applied down to elevation - 15.0' on the precast prestressed piles and only to exposed areas of the girder and piles that were not encased in CIP concrete.

Chem-Trete Silane, (Alkyl-Alkoxy Silane) sealer, manufactured by Dynait-Nobel, Moutville, N.J., was selected for this structure. This sealer was to be applied in one coat as specified by the manufacture, following proper curing of the concrete, and the removal of the surface laitance.

The preparation of the concrete surface, application method and rate of application, workability of the sealer, uniformity of appearance and problems were monitored for post construction reporting.

Construction Summary

The precast components of the structure were constructed by Concrete Technology, Tacoma, Washington. The Chem-Trete Silane was applied by Global Spraying at the Concrete Technology construction site after the concrete was properly cured. Prior to the sand blasting to remove surface laitance, the WSDOT Bridge Construction Engineer directed the prime contractor to conduct a test application of the Chem-Trete Silane, without surface preparation, to determine the rate of application and sealer penetration. As a result of this test, it was determined that the manufacture's specified coverage and penetration could be achieved without sandblasting by applying multiple coats of the sealer. A change order was issued to delete sandblasting from the contract specifications. Based on the test results the contractor applied two coats of sealer at a rate of 150 sq. ft. per gallon. This coverage was equal to that specified by the manufacture (125 - 175 sq. ft./2 gal.). The sealer was sprayed on the girders and piles during dry and light misty rain conditions. The spraying was discontinued during heavier showers. Due to weather conditions it took over two months to complete the spraying.

The Chem-Trete Silane Sealer appeared to be applied uniformly on all girders and piles. This was difficult to determine as the sealer is clear and cannot be seen after it

drys. The addition of colored pigment would make the sealer more visible and provide for easier inspection.

The unit cost for the sealer and the spraying in place was \$4.50/square yard. There were approximately 22,450 square yards covered.

Tests and Evaluations

The spraying of the Chem-Trete Silane Sealer was inspected to ensure that manufacture's specifications were met.

The WSDOT Materials Laboratory conducted electrical resistivity tests on the treated beams. Numerous tests were performed and each revealed that there was no apparent barrier between the reinforcing steel and the copper plate used in the resistivity test. It was noted that the low range of the readings, 600 to 1500 ohms, seemed to indicate that the passage of electricity was enhanced by the Chem-Trete Silane.

The electrical resistivity test did not indicate that the Chem-Trete coating provided a waterproof membrane, but this does not necessarily mean that the coating will not prevent the ingress of chloride salts. As the manufacture's literature points out, the Chem-Trete coating is not a barrier to water vapor. The electrical resistivity test, in

this case, was not a good test method to measure the effectiveness of this type of sealer.

To date, there has been no noticeable signs of deterioration due to the penetration of chloride ions. The structure has been exposed to the marine environment for over one and a half years. Continued evaluation will be done as part of WSDOT's bridge inspection program.

Conclusions

1. Chem-Trete Silance can be applied by spraying, to comply with manufacture's specification by using two coats.
2. Removal of surface laitance is not required prior to applying the silane sealer, provided two or more coats are applied.
3. This sealer is clear when applied and dries to the same color as the concrete.
4. The unit cost for placement of the sealer was \$4.50/square yard.

5. Electrical resistivity test does not provide information on the sealer's ability to ward off chloride ions.
6. After one and a half years in a marine environment, the Naselle River Bridge (10/24) showed no sign of deterioration caused by chloride ion penetration to the reinforcing steel.

Recommendations

1. A colored pigment added to the Chem-Trete Silane Sealer would make it easier to inspect for proper coverage.
2. The electrical resistivity test should not be used as a test method for Chem-Trete Silane.
3. A field test method should be developed for measuring the ability of sealants to prevent the intrusion of chloride ions into concrete.
4. Naselle River Bridge should be inspected annually and reported to the Washington State Department of Transportation Materials Laboratory for follow up analysis.

5. Future application of Chem-Trete Silane Sealer or other similar sealers should be monitored as experimental features to provide additional data on their effectiveness.